

## Specification of PU based sealant

ANNEXURE

1	Shelf Life	12 months
2	Cure system	Moisture curing
3	Rate of cure	3 mm cure approx. per 24 hrs
4	Tensile Strength	1.8 N/mm <sup>2</sup> approx.
5	Lap shear strength	1.5N/mm <sup>2</sup>
6	Density	1.3kg/ltr approx. depending On colour
7	Glass Transition Temperature	-45°C Approx.
8	Elongation at Break	500 % Approx.
9	Shrinkage	5% Approx.
10	Chemical Base	1-C polyurethane
11	Application Temperature	5°C to 40°C
12	Service temperature	-40°C to 90°C

AVINASH  
KUMAR  
SINGH  
CDO/TATA

Digitally signed  
by AVINASH  
KUMAR SINGH  
Date:  
2025.08.08  
12:09:01 +05'30'



वरिष्ठ खण्ड अभियन्ता (डीजल)  
द० पू० रेलवे, खड़गपुर कारखाना  
Sr. Section Engineer (Diesel)  
S.E. Railway / Kharagpur Workshop

RAKESH  
KUMAR  
SSE/C&W/TATA

Digitally signed  
by RAKESH  
KUMAR  
Date: 2025.08.08  
12:08:32 +05'30'